

TECHNICAL DATA SHEET

PINTYPLUS BASIC SYNTHETIC MATT PAINT



1. Description

Pinty Plus BASIC matt paint is a quick dry synthetic enamel. It provides high resistance outdoors and an excellent adherence on a large range of materials.

2. Properties:

- Great adherence
- High hiding power
- Good colour retention
- Excellent resistance outdoors
- Great hardness and flexibility
- Very easy application
- It contains neither lead nor chromates



* Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

**The information about the level of volatile substances emissions inside a room state a toxicity risk by inhalation, in a scale ranging from A+ (very light emissions) to C (strong emissions)*

3. Recommended uses:

Suitable for use both indoors and outdoors. Recommended to project and decorate any kind of supports: metal, cardboard, stone, ceramics and many kinds of plastics. Ideal for D I Y, industry, automotion, plumbing ...

4. Presentation

Colours: White M103 and Balck M106

Cans: 520cc/400 ml and 270cc/200ml cans.

5. Technical Characteristics:

- Nature Modified alkydic resin

• Pigments	Great solidity to the light
• Solvents	Aromatics and ketones
• Propellant	Hydrocarbons, rich in C3 y C4
• Density	0.98 ± 0.02 gr./cc (Depending on the colour)
• Viscosity	18 – 20 seg. (Ford Cup Nr. 4, 20°C)
• % solids in weight	33 ± 5 % (Theoretical value)
• VOC	610± 10 gr./l (Depending on the colour)
• Gloss at 60°	< 5
• Spreading:	520/400ml: 2 m ² according to support 270/200ml: 1 m ² according to support
• Drying time at 20°C:	Superficial: 1 hour Total: 2 hours Repainted: Before 1 hour or after 48 hours.
• Application temperature	from 10 up to 35°C
• Paint resistance to the heat	Recommended up to 90°C
• Flammability	Extremely flammable
• Pressure:	3-4 bars at 20°C 6-7 bars at 50°C
• Cleaning	Cleaning solvent in spray
• Life of the product	> 3 years

6. Instructions

The surface to be painted should be clean, dry and without any kind of pollutant. In order to obtain an optimal finish, treat the surface with a primer, a sealant or a suitable anchorage coating.

Shake the can well during 1 minute after hearing the ball rattles. Spray at a distance for 25/30 minutes applying thin, quick and criss-cross layers. In order to achieve a uniform finish and avoid any paint hang, it is advisable to apply two thin coats instead of a thick one. At the end of the application, turn the can over and spray until only gas comes out.

7. Security

The aerosol can features the correspondent security indications which must be followed. For further information please check the Security Data Sheet.

The information provided in the present technical sheet is the result of the research undertaken in our laboratory as well as real experiences based on applications. Nevertheless due to the fact that quite often the

products are used in conditions beyond our control, we cannot warranty the good results of the product if the application and use are not the correct ones.



NOVASOL SPRAY S. A.

Polígono Industrial Empalme
C/ Empalme, 27
Tel. 977 67 76 05 Fax. 977 67 80 72
43712 LLORENÇ DEL PENEDÈS (Tarragona)
novasol@novasolspray.com